




tesa[®] 4785 Bond & Detach

Product Information

50 µm d/s High Shock Transfer Tape



Product Description

tesa[®] 4785 is a 50 µm single layer transfer mounting tape with a special high shock adhesive and doubled PET liner

Product Features

- Thickness: 50µm
- Outstanding shock resistance
- High bonding strength
- High tack and quick wetting on LSE substrates
- High push out resistance
- Very good die-cutability
- Residue free removability

Application Fields

- Mounting of components in electronic devices even on LSE substrates
- Battery mounting

Technical Information (average values)

The values in this section should be considered representative or typical only and should not be used for specification purposes.

Product Construction

- | | | | |
|--------------------|-----------|----------------------|-------------|
| • Backing | none | • Color | translucent |
| • Type of adhesive | specialty | • Color of liner | transparent |
| • Type of liner | PET | • Thickness of liner | 50 µm |
| • Total thickness | 50 µm | | |

Properties/Performance Values

- | | | | |
|-------------------------------------|-----------|-------------------------------------|-----------|
| • Removability after 14 days (23°C) | very good | • Static shear resistance at 40°C | very good |
| • Residue-free removability | yes | • Temperature resistance long term | 60 °C |
| • Static shear resistance at 23°C | very good | • Temperature resistance short term | 90 °C |



tesa[®] 4785

Bond & Detach

Product Information

Adhesion to Values

• Aluminium (initial)	5.5 N/cm	• PET (initial)	5.5 N/cm
• Aluminium (after 14 days)	6 N/cm	• PET (after 14 days)	6 N/cm
• Magnesium (initial)	4.5 N/cm	• Steel (initial)	6.5 N/cm
• Magnesium (after 14 days)	5 N/cm	• Steel (after 14 days)	7 N/cm

Storage Conditions

Storage Conditions

The optimal storage conditions are as follows:

- Temperature range [°C]: 23±2 (Standard ISO 554)
- Humidity range [%]: 50±5 (Standard)

Please ensure that these conditions are maintained to guarantee the quality and shelf life of the product.

Disclaimer

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All information and recommendations are provided to the best of our knowledge on the basis of our practical experience. Nevertheless tesa SE can make no warranties, express or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. Therefore, the user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

For latest information on this product please visit <http://l.tesa.com/?ip=04785>